



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 9/14, 9/30, 9/36, 47/00, 47/02, 47/30, B05D 3/00	A1	(11) International Publication Number: WO 99/03449 (43) International Publication Date: 28 January 1999 (28.01.99)
(21) International Application Number: PCT/US98/14830 (22) International Filing Date: 16 July 1998 (16.07.98) (30) Priority Data: 08/895,484 16 July 1997 (16.07.97) US (71) Applicant: BERWIND PHARMACEUTICAL SERVICES, INC. [US/US]; Moyer Boulevard, West Point, PA 19086 (US). (72) Inventors: GRILLO, Susan, M.; 1042 Birch Street, Lansdale, PA 19446 (US). KORCHOK, Brian; 1811 Supplee Road, Lansdale, PA 19446 (US). KINSEY, Bruce; 436 Store Road, Harleysville, PA 19438 (US). HARTMAN, Melanie; 49 Diamond Street, Souderton, PA 18964 (US). PORTER, Stuart, C.; 675 Brighton Drive, Hatfield, PA 19440 (US). STEFFENINO, Rita; 3722 Gerryville Pike, Green Lane, PA 18054 (US). REYES, George; 1710 Morris Court, North Wales, PA 19454 (US). BURKE, Thomas, J.; Apartment 833, 777 West Germantown Pike, Plymouth Meeting, PA 19462 (US).		(74) Agents: EARLEY, John, F., A. et al.; Harding, Earley, Follmer & Frialety, 86 The Commons at Valley Forge East, 1288 Valley Forge Road, P.O. Box 750, Valley Forge, PA 19482-0750 (US). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: BRIGHT WHITE FILM COATINGS AND FILM COATING COMPOSITIONS THEREFOR (57) Abstract <p>A dry film coating composition used to make a bright white film coating for nutritional supplements, pharmaceutical tablets, and the like, comprises dextrose, an auxiliary film-former, and titanium dioxide. Optionally, but advantageously, the coating composition also may include one or more of the following components: a plasticizer, a surfactant, a flow aid, and a preservative.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**BRIGHT WHITE FILM COATINGS AND FILM COATING
COMPOSITIONS THEREFOR**

Background of the Invention

1. Field of the Invention

This invention relates to the field of aqueous film coating of nutritional supplements and pharmaceutical tablets, and is specifically concerned with providing bright white film coatings based on dextrose for coating nutritional supplements, such as vitamin tablets and calcium/oyster shell tablets, and pharmaceutical tablets, such as acetaminophen (APAP), aspirin (ASA), and Ibuprofen.

2. Description of the Prior Art

Hydroxypropyl methylcellulose (HPMC) has been used in coatings for substrates such as pharmaceutical tablets. For example, such coatings, including white coatings (coatings containing titanium dioxide as the colorant), made from coating compositions manufactured

by Colorcon and disclosed in U.S. Patent Nos. 4,543,370 and 4,683,256, said patents being incorporated herein by reference, have proven especially effective when used on pharmaceutical tablets.

5 However, in the pharmaceutical and nutritional supplement industries, it is desired to provide some pharmaceuticals, such as APAP and Ibuprofen, and some nutritional supplements with a white coating that is brighter than the white coatings obtained using HPMC-based coating compositions.

10

SUMMARY OF THE INVENTION

It is an object of the invention to provide a white film coating for vitamin tablets, calcium/oyster shell tablets, and pharmaceutical tablets that is brighter than the white film coatings obtained using HPMC-based coating compositions.

15

These and other objects are accomplished by our invention, which is described below.

DETAILED DESCRIPTION OF THE INVENTION

20 In accordance with the invention, our dry film coating compositions for use in forming coating dispersions for film coating nutritional supplements, pharmaceutical tablets, and the like, comprise dextrose, an auxiliary film former, and titanium dioxide.

5

Advantageously, the inventive dry film coating

compositions may include one or more of the following components: a plasticizer, a surfactant, a flow aid, and a preservative.

5 In accordance with the invention, a method of coating substrates such as nutritional supplements, pharmaceutical tablets, and the like, comprises mixing dextrose, an auxiliary film-former, and titanium
10 dioxide into water to form an inventive aqueous coating dispersion, applying the inventive coating dispersion onto said substrates to form a white film coating on said substrates, and drying the white film coating on said substrates. Optionally, but advantageously, the following components may be mixed into water with the
15 dextrose, the auxiliary film-former, and the titanium dioxide to form the inventive coating dispersion: a plasticizer, a surfactant, a flow aid, and a preservative.

20 The invention also includes the coated substrates, such as coated vitamins, coated calcium/oyster shell tablets, and coated pharmaceutical tablets, the aqueous coating dispersion formed from the inventive dry film coating composition or from the components of said composition, the method of making the dry film coating compositions and the method of making the coating
25 dispersions of the invention.

The primary film-former of the inventive dry film coating composition and of the inventive aqueous coating dispersion is dextrose.

The preferred range for dextrose is about 20% to about 50% by weight of the inventive dry film coating composition and of the non-water ingredients of the inventive aqueous coating dispersion. More preferably, the range for dextrose is about 25% to about 35% by weight of the inventive dry film coating composition and of the non-water ingredients of the inventive aqueous coating dispersion.

The auxiliary film-former may be polyvinylpyrrolidone (PVP), hydroxypropyl methylcellulose, methylcellulose, hydroxypropyl cellulose (HPC), sodium carboxymethylcellulose (sodium CMC), maltodextrin, polydextrose, modified food starch, modified food starch with corn syrup solids, starch (e.g., STARCH 1500 starch), tapioca dextrin, lactose, sodium alginate, PG alginate, gum acacia, polyvinyl alcohol (PVA), any of the film coating polymers recited in Colorcon U.S. Patent No. 4,543,370, which is incorporated herein by reference, and combinations thereof. The auxiliary film-former(s) act as strength enhancers for the film coating. Their presence in the coatings help prevent cracking of the film coating, as well as helping to prevent edge wear/chipping of the coated tablet. A preferred auxiliary film-former is sodium CMC. The preferred and the more preferred ranges for the auxiliary film-former(s) by weight of the inventive dry film forming composition and by weight of the non-water ingredients of the inventive

aqueous coating dispersion are 1% to 50% (preferred) and 10% to 20% (more preferred). The preferred ranges and the more preferred ranges for various exemplary auxiliary film-former(s) are set out below.

5 The preferred range and the more preferred range for the titanium dioxide (TiO_2) are 25% to 50% (preferred) and 30% to 40% (more preferred) by weight of the inventive coating composition and by weight of the non-water ingredients of the inventive coating
10 dispersion.

Exemplary of the plasticizer are mineral oil, polyethylene glycol having a molecular weight in the range of 200 to 8000, propylene glycol, glycerine, triacetin, acetyltriethyl citrate, triethyl citrate
15 (Citroflex A2), tributylcitrate (Citroflex 4), and acetyltributylcitrate (Citroflex A4), and the preferred ranges for the plasticizer are set out below, together with preferred and more preferred ranges for various exemplary plasticizers.

20 Exemplary of the surfactant is Polysorbate 80, and the preferred ranges for the surfactant are set out below, together with preferred and more preferred ranges for an exemplary surfactant.

15 Exemplary of the flow aid is stearic acid, and the preferred ranges and the more preferred ranges for the flow aid are set out below, together with the preferred and the more preferred ranges for stearic acid.

Exemplary of the preservative is sodium citrate,

and the preferred ranges for the preservative are set out below, together with the preferred and the more preferred ranges for sodium citrate.

AUXILIARY FILM FORMERS

5	Preferred	1-50%
	More Preferred	10-20%
PVA		
	Preferred	0-10%
	More Preferred	3-6%
10	PVP	
	Preferred	0-10%
	More Preferred	3-6%
HPMC/Methylcellulose/ HPC		
15	Preferred	0-50%
	More Preferred	5-50%
	Even More Preferred	10-20%
Polydextrose		
0	Preferred	0-50%
	More Preferred	5-50%
	Even More Preferred	10-20%

Lactose

Preferred 0-20%

More Preferred 5-10%

Na CMC

5 Preferred 0-15%

More Preferred 1-15%

Even More Preferred 5-8%

10 Modified Food Starch/
Modified Food Starch with Corn Syrup Solids/
Starch 1500

Preferred 0-15%

More Preferred 1-15%

Even More Preferred 5-8%

Maltodextrin

15 Preferred 0-50%

More Preferred 5-50%

Even More Preferred 10-20%

Tapioca Dextrin

Preferred 0-5%

20 More Preferred 1-5%

Even More Preferred 3-5%

PG Alginate

Preferred 0-5%

More Preferred 3-5%

	Sodium Alginate	
	Preferred	0-5%
	More Preferred	3-5%
	Gum Acacia	
5	Preferred	0-5%
	More Preferred	3-5%
	SURFACTANT	
	Preferred	0-5%
	Polysorbate 80	
10	Preferred	0-5%
	More Preferred	0.5-1%
	FLOW AID	
	Preferred	0-15%
	More Preferred	5-10%
15	Stearic Acid	
	Preferred	0-15%
	More Preferred	5-10%
	PLASTICIZER	
	Preferred	0-20%
20	Mineral Oil	
	Preferred	0-15%
	More Preferred	3-5%

SUBSTITUTE SHEET (RULE 26)

Polyethylene Glycol 8000

Preferred 0-20%

More Preferred 5-10%

Glycerine

5 Preferred 0-15%

More Preferred 5-10%

PRESERVATIVE

Preferred 0-5%

More Preferred 2-3%

10 Sodium Citrate

Preferred 0-5%

More Preferred 2-3%

15 The ranges set out above are all by weight of the dry film coating composition of the invention and of the non-water ingredients of the aqueous coating dispersion of the invention.

The following examples illustrate the invention, all ingredients being by weight.

EXAMPLE 1

20 The dry components of the following formulation were blended together for five minutes in a PK Blender (Paterson Kelly) to form a mixture. Then, the liquid

components were added to the mixture of dry components via the I-bar of the blender and blended therein by mixing for an additional five minutes to form a dry film coating composition of the invention.

5 Optionally, the composition may be milled such as in a hammer mill (Apex Machinery, Dartford, England), for example.

10 Optionally, the dry film coating composition may be granulated using a planetary mixer, such as a Hobart planetary mixer. To accomplish this, the dry film coating composition is loaded into the mixer and the mixer is switched on, and sufficient water is slowly added until the composition forms slightly adherent granules. These granules are then passed through a 1-2
15 mm screen and then dried in a 30°C oven until the moisture content is below 5%. The composition is then sieved again through a 1-2 mm screen and is then ready for use in a non-dusting, granular form. Other methods of granulation, such as spray granulation and roller
20 compaction, also may be used.

25 450 grams of the resulting film coating composition was dispersed into 1800 grams of distilled water (about 30 minutes) to form an inventive coating dispersion (20% solids), and all of the dispersion was sprayed using a 24" Accela Cota coater (Thomas Engineering) onto 15000 grams of vitamin tablets (Pharmavite) to form an inventive coating thereon having a theoretical weight gain of 3.0%.

This produced a bright white film coating on the tablets.

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	32.0%	1600.00
5	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
	Polyethylene Glycol 8000 (Union Carbide)	8%	400.00
10	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
	Mineral Oil (Pennreco)	3%	150.00
15	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
		100%	5000.00

EXAMPLE 2

Example 1 was repeated, except that the dispersion was sprayed onto 15000 grams of APAP tablets. This produced a bright white film coating on the APAP tablets.

EXAMPLE 3

Example 1 was repeated, except that the film coating composition had the following formulation:

12

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	26.0%	1300.00
	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
5	Polyethylene Glycol 400 (Union Carbide)	8%	400.00
	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
10	Stearic Acid (Humco)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
	Mineral Oil (Pennreco)	3%	150.00
15	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
		100%	5000.00

This produced a bright white film coating on the tablets.

20 EXAMPLE 4

Example 2 was repeated, except that the film coating composition had the formulation of Example 3. This produced a bright white film coating on the APAP tablets.

25 EXAMPLE 5

The dry components of the following formulation were blended together for five minutes in a food processor to form a mixture. Then, the liquid components of the formulation were added to the mixture of the dry components and blended therein by mixing for

0

SUBSTITUTE SHEET (RULE 26)

an additional five minutes to form a film coating composition of the invention.

Optionally, the coating composition may be granulated or milled.

5 9.0 grams of the resulting film coating composition was dispersed into 36.0 grams of distilled water and stirred until dispersed to form an inventive coating dispersion (20% solids), and all of the dispersion was sprayed using an Aeromatic Strea 1
10 coater (Niro) onto 300 grams of 3/8" concave white placebos to form an inventive coating thereon having a theoretical weight gain of 3.0%.

This produced a bright white film coating on the tablets.

15	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	26.0%	1300.00
	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
20	Polyethylene Glycol 400 (Union Carbide)	8%	400.00
	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Stearic Acid (Humco)	6%	300.00
25	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
	Mineral Oil (Pennreco)	3%	150.00
	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
30		100%	5000.00

SUBSTITUTE SHEET (RULE 26)

Examples 6-19 further illustrate the invention, all percentages being by weight. In Examples 6-19, the components of each formulation are mixed together, formed into a coating dispersion, and applied to 3/8" concave white placebos, as in Example 5, to obtain bright white film coatings.

EXAMPLE 6

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	35.0%	1750.00
10	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
	Glycerin	5%	250.00
	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
15	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
	Mineral Oil (Pennreco)	3%	150.00
	Titanium dioxide (water) (Kronos)	32%	1600.00
20	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
		100%	5000.00

EXAMPLE 7

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	35.0%	1750.00
25	Methycellulose	15%	750.00
	Glycerin (DOW)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00

15

Mineral Oil (Pennreco)	3%	150.00
Titanium dioxide (water) (Kronos)	32%	1600.00
Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
	100%	5000.00

5

EXAMPLE 8

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	20.0%	200.00
	Methycellulose	14%	140.00
	Sodium CMC (Aqualon)	8%	80.00
10	Stearic Acid (Humco)	8%	80.00
	Tapioca Dextrin (Staley)	5%	50.00
	Glycerin (DOW)	2%	20.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	30.00
15	Titanium dioxide (water) (Kronos)	<u>40%</u>	<u>400.00</u>
		100%	1000.00

EXAMPLE 9

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	20.0%	200.00
20	Methycellulose (DOW)	14%	140.00
	Tapioca Dextrin (Staley)	5%	50.00
	Sodium CMC (Aqualon)	8%	80.00
	Polydextrose (Pfizer)	8%	80.00
	Glycerin (DOW)	2%	20.00
25	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	30.00
	Titanium dioxide (water) (Kronos)	<u>40%</u>	<u>400.00</u>
		100%	1000.00

EXAMPLE 10**SUBSTITUTE SHEET (RULE 26)**

16

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	25.0%	250.00
	Methycellulose (DOW)	14.0%	140.00
	Sodium CMC (Aqualon)	8%	80.00
5	PURITY 4* (National Starch and Chemical Company)	8%	80.00
	Glycerin (DOW)	2%	20.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	30.00
10	Titanium dioxide (water) (Kronos)	<u>40%</u>	<u>400.00</u>
		100%	1000.00

***Purity 4 is a modified food starch with Tapioca as its source.**

EXAMPLE 11

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
15	Dextrose (Staley)	25.0%	250.00
	Methycellulose (DOW)	14.0%	140.00
	Sodium CMC (Aqualon)	8%	80.00
20	PURITY HO** (National Starch and Chemical Company)	8%	80.00
	Glycerin (DOW)	2%	20.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	30.00
	Titanium dioxide (water) (Kronos)	<u>40%</u>	<u>400.00</u>
25		100%	1000.00

****Purity HO is modified Food Starch and dried Glucose Syrup with waxy maize as its source.**

EXAMPLE 12

<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
------------------	--------------------	--------------

SUBSTITUTE SHEET (RULE 26)

17

	Dextrose (Staley)	25.0%	250.00
	Methycellulose (DOW)	14.0%	140.00
	Sodium CMC (Aqualon)	8%	80.00
5	PURITY GUM 59*** (National Starch and Chemical Company)	8%	80.00
	Glycerin (DOW)	2%	20.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	30.00
	Titanium dioxide (water) (Kronos)	<u>40%</u>	<u>400.00</u>
10		100%	1000.00

***Purity GUM 59 is a modified food starch with waxy maize as its source

EXAMPLE 13

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
15	Dextrose (Staley)	29.0%	1450.00
	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
	Polyethylene Glycol 8000 (Union Carbide)	8%	400.00
20	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
25	Mineral Oil (Pennreco)	3%	150.00
	Gum Acacia (Colloides Naturels, Inc.)	3%	150.00
	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
30		100.0%	5000.00

SUBSTITUTE SHEET (RULE 26)

EXAMPLE 14

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	25.0%	250.00
	Methycellulose (Dow)	14.0%	140.00
5	Sodium CMC (Aqualon)	8.0%	80.00
	Starch 1500 (Colorcon)	8.0%	80.00
	Glycerin (Dow)	2.0%	20.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3.0%	30.00
10	Titanium dioxide (water) (Kronos)	<u>40.0%</u>	<u>400.00</u>
		100.0%	1000.00

EXAMPLE 15

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	29.0%	1450.00
15	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
	Polyethylene Glycol 8000 (Union Carbide)	8%	400.00
20	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
	Mineral Oil (Pennreco)	3%	150.00
25	PG Alginate (Kelco)	3%	150.00
	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
		100.0%	5000.00

EXAMPLE 16

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
30	Dextrose (Staley)	29.0%	1450.00

19

	HPMC/Pharmacoat E-50 (DOW/ShinEtsu)	10%	500.00
	Polyethylene Glycol 8000 (Union Carbide)	8%	400.00
5	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	5%	250.00
	Sodium CMC (Aqualon)	6%	300.00
	Sodium Citrate, Anhydrous (ADM Corn Processing)	3%	150.00
10	Mineral Oil (Pennreco)	3%	150.00
	Sodium Alginate (Kelco)	3%	150.00
	Titanium dioxide (water) (Kronos)	32%	1600.00
	Polysorbate 80 (ICI Surfactants)	<u>1%</u>	<u>50.00</u>
		100.00	5000.00

15 **EXAMPLE 17**

	<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
	Dextrose (Staley)	40%	480.00
	HPMC/Pharmacoat E-15 (DOW/ShinEtsu)	28%	280.00
20	Titanium Dioxide (water) (Kronos)	<u>32%</u>	<u>320.00</u>
		100%	1000.00

SUBSTITUTE SHEET (RULE 26)

EXAMPLE 18

<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
Dextrose (Staley)	40%	400.00
5 HPMC/Pharmacoat E-15 (Dow/ShinEtsu)	18%	180.00
PEG 8000	10%	100.00
Titanium Dioxide (water) (Kronos)	<u>32%</u> 100%	<u>320.00</u> 1000.00

EXAMPLE 19

<u>Component</u>	<u>Percentages</u>	<u>Grams</u>
Dextrose (Staley)	29.9%	299.0
HPMC/Pharmacoat E-15 (Dow/ShinEtsu)	10.0%	100.0
15 Polyethylene Glycol 8000 (Union Carbide)	8.0%	80.0
HPMC/Pharmacoat E-50 (Dow/ShinEtsu)	5.0%	50.0
Sodium CMC (Aqualon)	8.0%	80.0
20 Mineral Oil (Pennreco)	3.0%	30.0
Sodium Citrate, Anhydrous (ADM Corn Processing)	3.0%	30.0
Tapioca dextrin (Staley)	0.1%	1.0
Titanium dioxide (water) (Kronos)	32.0%	320.0
25 Polysorbate 80 (ICI Surfactants)	<u>1.0%</u> 100.0%	<u>10.0</u> 1000.0

EXAMPLE 20

Example 1 was repeated, except that the dispersion was sprayed onto 15000 grams of oyster shell substrates. This produced a bright white film coating on the oyster shell substrates.

Although it is preferred to make the coating dispersions of the invention from the inventive dry film coating compositions, the inventive coating dispersions may be made by adding the individual components of the inventive dry film coating composition to water to form the inventive coating dispersions.

ADVANTAGES

The invention provides a film coating that possesses good film adhesion and a smooth surface.

Moreover, the invention produces a bright white film coating that is noticeably brighter than white film coatings produced using HPMC-based coating compositions.

Claims:

1. A dry film coating composition for forming a
coating dispersion for film coating nutritional
supplements, pharmaceutical tablets, and the like,
5 comprising

dextrose,
an auxiliary film-former, and
titanium dioxide.

2. The composition of claim 1,
10 the dextrose being 20% to 50% by weight of the
composition.

3. The composition of claim 1,
the dextrose being 25% to 35% by weight of the
composition.

4. The composition of claim 1,
15 the auxiliary film-former being
polyvinylpyrrolidone (PVP), hydroxypropyl
methylcellulose, methylcellulose, hydroxypopyl
cellulose (HPC), sodium carboxymethylcellulose (Sodium
20 CMC), polydextrose, starch, modified food starch,
modified food starch with corn syrup solids, tapioca
dextrin, lactose, maltodextrin, sodium alginate, PG
alginate, gum acacia, polyvinyl alcohol (PVA), and
combinations thereof.

5. The composition of claim 1, the auxiliary film-former being in a range of 1% to about 50% by weight of the composition.

6. The composition of claim 1, the auxiliary film-former being in a range of 10% to about 20% by weight of the composition.

7. The composition of claim 1, the titanium dioxide being in a range of about 25% to about 50% by weight of the composition.

8. The composition of claim 1, the titanium dioxide being in a range of about 30% to about 40% by weight of the composition.

9. The composition of claim 1, further including a plasticizer.

10. The composition of claim 9, the plasticizer being mineral oil, polyethylene glycol, propylene glycol, glycerine, triacetin, acetyltriethyl citrate, triethyl citrate, tributylcitrate, or acetyltributylcitrate.

11. The composition of claim 9, the plasticizer being in a range of greater than 0% to about 20% by weight of the composition.

12. The composition of claim 9,
the plasticizer being in a range of 5% to 10% by
weight of the composition.

13. The composition of claim 9,
the plasticizer being in a range of 3% to 5% by
weight of the composition.

14. The composition of claim 1, further including
a surfactant.

15. The composition of claim 14,
the surfactant being polysorbate 80.

16. The composition of claim 14,
the surfactant being in a range of greater than 0%
to about 5% by weight of the composition.

17. The composition of claim 14,
the surfactant being in a range of greater than
0.5% to about 1% by weight of the composition.

18. The composition of claim 1, further including
a flow aid.

19. The composition of claim 18,
the flow aid being stearic acid.

20. The composition of claim 18,
the flow aid being in a range of greater than 0%
to about 15% by weight of the composition.

21. The composition of claim 18,
the flow aid being in a range of greater than 5%
to about 10% by weight of the composition.

22. The composition of claim 1, further including
a preservative.

23. The composition of claim 22,
the preservative being sodium citrate.

24. The composition of claim 22,
the preservative being in a range of greater than
0% to about 5% by weight of the composition.

25. The composition of claim 22,
the preservative being in a range of about 2% to
about 3% by weight of the composition.

26. The composition of claim 1, further including
a plasticizer,
the plasticizer being mineral oil, polyethylene
glycol, propylene glycol, glycerine, triacetin,
acetyltriethyl citrate, triethyl citrate,
tributylcitrate, or acetyltributylcitrate, and

the plasticizer being in a range of greater than 0% to about 20% by weight of the composition,

the dextrose being 20% to 50% by weight of the composition,

5 the auxiliary film-former being
polyvinylpyrrolidone (PVP), hydroxypropyl
methylcellulose, methylcellulose, hydroxypopyl
cellulose (HPC), sodium carboxymethylcellulose (Sodium
CMC), polydextrose, starch, modified food starch,
10 modified food starch with corn syrup solids, tapioca
dextrin, lactose, maltodextrin, sodium alginate, PG
alginate, gum acacia, polyvinyl alcohol (PVA), and
combinations thereof,

the auxiliary film-former being in a range of 1%
15 to about 50% by weight of the composition, and

the titanium dioxide being in a range of about 25%
to about 50% by weight of the composition.

27. The composition of claim 26, further
including

20 a surfactant,
the surfactant being polysorbate 80, and
the surfactant being in a range of greater than 0%
to about 5% by weight of the composition,

a flow aid,
25 the flow aid being stearic acid, and
the flow aid being in a range of greater than 0%
to about 15% by weight of the composition, and

a preservative,
the preservative being sodium citrate, and
the preservative being in a range of greater than
0% to about 5% by weight of the composition.

5 28. A method of coating substrates such as
nutritional supplements, pharmaceutical tablets, and
the like, with a white film coating comprising the
steps of

 mixing dextrose, and auxiliary film-former, and
10 titanium dioxide into water to form an aqueous coating
dispersion,

 applying an effective amount of said coating
dispersion onto said substrates to form a white film
coating on said substrates, and

15 drying the white film coating on said substrates.

29. The method of claim 28, including dispersing
a plasticizer into the aqueous coating dispersion.

30. The method of claim 28, including dispersing
a surfactant into the aqueous coating dispersion.

20 31. The method of claim 28, including dispersing
a flow aid into the aqueous coating dispersion.

32. The method of claim 28, including dispersing

a preservative into the aqueous coating dispersion.

33. The method of claim 28,

the dextrose being in a range of about 20% to about 50% by weight of the non-water ingredients of the dispersion,

the auxiliary film-former being in a range of about 1% to about 50% by weight of the non-water ingredients of the dispersion, and

the titanium dioxide being in a range of about 25% to about 50% by weight of the non-water ingredients of the dispersion.

34. The method of claim 28,

the dextrose being in a range of about 25% to about 35% by weight of the non-water ingredients of the dispersion,

the auxiliary film-former being in a range of about 10% to about 20% by weight of the non-water ingredients of the dispersion, and

the titanium dioxide being in a range of about 30% to about 40% by weight of the non-water ingredients of the dispersion.

35. The method of claim 33, further including a plasticizer,

the plasticizer being mineral oil, polyethylene glycol, propylene glycol, glycerine, triacetin,

acetyltriethyl citrate, triethyl citrate,
tributylcitrate, or acetyltributylcitrate, and

the plasticizer being in a range of greater than
0% to about 20% by weight of the non-water ingredients
of the dispersion.

36. The method of claim 35, further including
a surfactant,
the surfactant being polysorbate 80, and
the surfactant being in a range of greater than 0%
to about 5% by weight of the non-water ingredients of
the dispersion,

a flow aid,
the flow aid being stearic acid, and
the flow aid being in a range of greater than 0%
to about 15% by weight of the non-water ingredients of
the dispersion, and

a preservative,
the preservative being sodium citrate, and
the preservative being in a range of greater than
0% to about 5% by weight of the non-water ingredients
of the dispersion.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US98/14830

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : A61K 9/14, 9/30, 9/36, 47/00, 47/02, 47/30; B05D 3/00

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 427/2.14,2.23 ; 424/439,440,441,442, 458,459, 463,464,465,474, 479,480,481,482,489, 493

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,543,370 A (PORTER et al.) 24 September 1985, see entire disclosure.	1-36
Y	US 5,641,536 A (LECH et al.) 24 June 1997, col.3, line 35-col.6, line 9; examples.	1-36
Y	US 5,370,881 A (FUISZ) 06 December 1994, col.3, line 2-col.4, line 65; col.7, lines 4-42; col.8, line 32-col.10, line 65; col.11, lines 47-63; col.12, line 37-66; examples.	1-36
Y	US 5,039,540 A (ECANOW) 13 August 1991, col.2, line 35-col.7, line 24.	22-25,32,36
Y	US 4,837,031 A (DENTON) 06 June 1989, see entire disclosure.	22-25,32,36



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
B earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

20 AUGUST 1998

Date of mailing of the international search report

26 OCT 1998

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

DIANA DUDASH

Telephone No. (703)308-2328

INTERNATIONAL SEARCH REPORT**International application No.**
PCT/US98/14830**C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,603,953 A (HERBIG et al.) 18 February 1997, col.11, line 31-col.13, line 11.	23,25,36

Form PCT/ISA/210 (continuation of second sheet)(July 1992)★

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US98/14830

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

427/2.14,2.23 ; 424/439,440,441,442, 458,459, 463,464,465,474, 479,480,481,482,489, 493